

Washer Based Open-End Cap







| Washer-Based Open-End Cap Nuts | | | | | | | | |
|--|--------|------------------------|-------|----------------|-------|----------------------|-------|--|
| Nominal Size or Basic Thread Diameter | | F | | N | | R | | |
| | | Width Across the Flats | | Overall Height | | Washer Base Diameter | | |
| | | Max | Min | Max | Min | Max | Min | |
| 10 | 0.1900 | 0.375 | 0.362 | 0.291 | 0.271 | 0.450 | 0.430 | |
| 1/4 | 0.2500 | 0.438 | 0.423 | 0.338 | 0.318 | 0.522 | 0.502 | |
| 5/16 | 0.3125 | 0.562 | 0.545 | 0.385 | 0.365 | 0.667 | 0.647 | |
| 3/8 | 0.3750 | 0.625 | 0.607 | 0.431 | 0.411 | 0.739 | 0.719 | |

| Description | A zinc alloy internally threaded fastener that features a wide-diameter, integral washer base and a low-crown cap with the top portion of its dome removed. | |
|---------------------------|---|--|
| Applications / Advantages | This design is preferred by some as a more attractive alternative to a basic hex nut. It is a useful alternative to a washer-based closed-enc nut because it can be used with bolts of any length. Washer-base design enables the nut to be used in oversized or offset holes, and with services such as wood or plastic. | |
| Material | Nuts are made from the zinc die cast alloy Zamak #3 which conforms to the following chemical composition requirements **Aluminum**: 3.5-4.3%; **Magnesium**: 0.02-0.05%; **Copper**: 0.25%** max.; Iron: 0.10% max.; **Lead**: 0.005% max.; **Cadmium**: 0.004% max.; **Tin**: 0.003% max.; **Zinc**: balance (*Note: Most commercial applications will accept copper content within the range of 0.25-0.75% without rejecting the product). | |